NAME: 2602TH00

1) Product Description: LDPE 2602TH00 high clarity Film

2) Application:

• Film, underblankets and films for medical applications. It is used in combination with LLDPE in products like diaper

3) Typical data. (Table)

| Property | Unit | Typical Value | Test Method |
|--------------------------|-------------------|---------------|--------------|
| Physical | | | |
| MFI | Dg/min | 1.9 | ISO 1133 |
| Density | kg/m ³ | 926 | ISO 1183 (A) |
| optical | | | |
| Haze | % | 7.1 | ASTM D1003A |
| Clarity | mV | 11 | DSM METHOD |
| Gloss | % | 61±5 | ASTM D2457 |
| Formulation | | | |
| Anti oxidant | ppm | 600±60 | DSM METHOD |
| Anti block | ppm | - | |
| slip | ppm | - | |
| Film property | | | |
| Impact Strength | kJ/m | 15 | ASTM D4272 |
| Tear Strength TD | KN/ m | 40 | ISO 6383-2 |
| Tear Strength MD | KN/ m | 90 | ISO 6383-2 |
| Yield Stress TD | MPa | 14 | ISO R527-1 |
| Yield Stress MD | MPa | 13 | ISO R527-1 |
| Tensile Strength TD | MPa | 20 | ISO R527-1 |
| Tensile Strength MD | MPa | 30 | ISO R527-1 |
| Elongation at break TD | % | >500 | ISO R527-1 |
| Elongation at break MD | % | >150 | ISO R527-1 |
| Modulus of elasticity TD | MPa | 260 | ISO R527-1 |
| Modulus of elasticity MD | MPa | 240 | ISO R527-1 |
| Co efficient of friction | | >1.0 | A STM D1894 |