## LD -LS0085

**1)Product Description:** LS0085 is a high molecular weight low density polyethylene film grade combining good flexible extrusion behavior and superior mechanical properties.

## 2) Applications:

• Thin shrink film

## 3) Typical data

**Film Properties** Film properties have been measured at  $45\mu m$  with a bur of 3.

| Properties                 | Value | Unit   | Test method  |
|----------------------------|-------|--------|--------------|
| MFR (190°C/2.16kg)         | 0.85  | Dg/min | ISO 1133     |
| Density                    | 0.921 | g/m³   | ISO 1183(A)  |
| Impact Strength            | 25    | KJ/m   | ASTM D 4272  |
| Tear Strength(TD)          | 30    | kN/m   | ISO 6383-2   |
| Tear Strength(MD)          | 40    | kN/m   | ISO 6383-2   |
| Yield Stress (TD)          | 11    | MPa    | ISO 527      |
| Yield Stress (MD)          | 11    | MPa    | ISO 527      |
| Strain at Break(TD)        | 500   | %      | ISO 527      |
| Strain at Break (MD)       | 200   | %      | ISO 527      |
| Modulus of Elasticity (TD) | 170   | MPa    | ISO 527      |
| Modulus of Elasticity (MD) | 170   | MPa    | ISO 527      |
| Coefficient of friction    | 1     | -      | ASTM D 1894  |
| Blocking                   | 50    | g      | Sabtec       |
| Re-blocking                | 50    | g      | Sabtec       |
| Haze                       | 9     | %      | ASTM D 1003A |
| Gloss                      | 55    | %      | ASTM D 2457  |
| Clarity                    | 30    | mV     | Sabtec       |

The above data are typical laboratory average . They are intended to serve as guides only.

## 4) Process conditions:

LS0085 is a grade with good toughness and good biaxial shrink properties. The material contains no additives, has a low energy consumption during processing and a good drawdown ability.

Producer: Arya Sasol Petrochemical Co.

Licensor: Sabtec CTR®

Packing: Supplied in pellet form and can be packaged in 25kg bags, 1 ton semi bulk or 17 ton bulk.