

S 30 S

1) Product Description :

This grade is for general injection molding applications .

2) Applications :

- Textile bobbins ,wheels ,fittings ,closures ,caps .

3) Typical data

Property	Unit	Typical Value	Test Method
M.F.I	Dg/min	1.8	ISO 1133
Density	g/cm ³	0.9	ISO 1183
Flexural Modulus	N/mm ²	1450	ISO 178
Tensile	N/mm ²	33	ISO R527
Elongation	%	13	ISO R527
Izod Impact	Kj/m ²	6.5	ISO 180
Hardness	point	71	ISO 868
Vicat	°C	155	ISO 306/A
H.D.T	°C	105	ISO 75/B

* Typical Values : not to be construed as specifications

Producer: Marun Petrochemical Co.

Licensor: Basell

Packing: 25 Kg plastic bag