



R.P.O (Rubber Process Oil)

| Specification | Rubber 250 | Rubber 290 |
|-------------------|------------|------------|
| V 100°C | 70 | 25 |
| Density 15°C | 1.050 | 1.010 |
| Flash Point, °c | 245 | 220 |
| aniline point, °c | 30 | 35 |
| VGC | 0.95 | 0.94 |
| RI at 70°C | 1.5600 | 1.5500 |
| BMCI | 109 | 87 |