

## TRAE

### Advantages:

Good abrasion resistance

Good low temperature flexibility

Low amounts of waste tires in the process

Good resistance to reversion

According to with international standards (EU 2005/69/EC)

Saving fuel and energy consumption

Extended tires life time

### Application:

This combination without harmful carbonic used as carrier oils, plasticizer, diluents & filling agent that remain in the final product contributing to both ease of processing and improved product performance in rubber industry.

Test method ASTM	TRAE	Characteristic
D-445	40	Kinematic viscosity @ 100 °C, cSt
D-92	250	Flash point , °C
D-97	42	Pour point , °C
D-1298	0.95	Specific gravity @ 15 , Kg/m <sup>3</sup>
IP-2	70	Aniline point, °C
D-2622	3	Sulphur content, Wt%
D-1500	7	Color
D-2501	0.875	Viscosity gravity constant (VGC)
IP 346	3	PCA content (DMSO), Wt%
D-3238	20	Carbon type analysis , %
	25	C <sub>A</sub>
	55	C <sub>N</sub>
		C <sub>P</sub>