

# UNBLEACHED RAFFIN WAX

## TYPICAL CHARACTERISTICS

Unbleached Paraffin Wax Grade	Oil Content %wt max.	Melting Point °C	Color Max.	Penetration 0.1mm@25°C	Viscosity @ 100°C (cSt)
	ASTM D-721	ASTM D-87	ASTM D-1500	ASTM D-1321	ASTM D-445
<b>M1</b>	<b>1</b>	<b>62-66</b>	<b>1</b>	<b>15-19</b>	<b>4.5-6.4</b>
<b>M2</b>	<b>2</b>	<b>62-66</b>	<b>1</b>	<b>15-19</b>	<b>4.5-6.4</b>
<b>M3</b>	<b>3</b>	<b>61-65</b>	<b>1</b>	<b>15-19</b>	<b>4.5-6.4</b>
<b>M5</b>	<b>5</b>	<b>60-65</b>	<b>1</b>	<b>15-19</b>	<b>4.5-6.4</b>
<b>M10</b>	<b>10</b>	<b>60-65</b>	<b>1</b>	<b>15-19</b>	<b>4.5-6.4</b>
<b>H1</b>	<b>1</b>	<b>68-71</b>	<b>4.5</b>	<b>-</b>	<b>6.5-8.0</b>
<b>H2</b>	<b>2</b>	<b>68-71</b>	<b>4.5</b>	<b>21-28</b>	<b>6.5-8.0</b>
<b>H3</b>	<b>3</b>	<b>68-71</b>	<b>4.5</b>	<b>21-28</b>	<b>6.5-8.0</b>
<b>H5</b>	<b>5</b>	<b>68-71</b>	<b>4.5</b>	<b>-</b>	<b>6.5-8.0</b>
<b>H10</b>	<b>10</b>	<b>66-69</b>	<b>4.5</b>	<b>-</b>	<b>6.5-8.0</b>

### Packaging

Slabs (20×50×4cm)

In carton (app.24 Kg)

Granules packed in one plastic bag in carton (app.16Kg)

